



## Products

### Angula 6x36 Class


- Fiber Core
- Galvanized
- 6x31WS
- 6x36WS
- 6x41WS
- 6x43SWS
- 6x49SWS




6x31WS




6x36WS



6x41WS



6x43SWS



6x49SWS

### 6x36 Class Fiber Core Strength & Weights Chart (inches)

Diameter (in)	Approx. Weight (lb/ft)	Minimum Breaking Force (lbs.)	
		IPS	EIPS
1/4	0.11	5,480	6,020
5/16	0.16	8,520	9,370
3/8	0.24	12,200	13,420
7/16	0.32	16,540	18,200
1/2	0.42	21,400	23,600
9/16	0.53	27,000	29,800
5/8	0.66	33,400	36,600
3/4	0.95	47,600	52,400
7/8	1.29	64,400	70,800
1	1.68	83,600	92,000
1 1/8	2.13	105,200	115,600
1 1/4	2.63	129,200	142,200
1 3/8	3.18	155,400	171,000
1 1/2	3.78	184,000	202,000
1 5/8	4.44	214,000	236,000
1 3/4	5.15	244,000	274,000
1 7/8	5.91	282,000	312,000
2	6.72	320,000	352,000

Reference Specifications: ASTM-A-1023; API 9A

### 6x36 Class Fiber Core Strength & Weights Chart (millimeters)

Diameter (mm)	Approx. Weight (kg/m)	Minimum Breaking Force (Metric Tons)	
		IPS	EIPS
6.35	0.16	2.5	2.7
7.94	0.24	3.9	4.3

9.53	0.36	5.5	6.1
11.11	0.48	7.5	8.3
13	0.63	9.7	10.7
14.5	0.79	12.2	13.5
16	0.98	15.1	16.6
19	1.41	21.6	23.8
22	1.92	29.2	32.1
26	2.50	37.9	41.7
29	3.17	47.7	52.4
32	3.91	58.5	64.5
35	4.73	70.5	77.6
38	5.63	83.5	91.6
42	6.61	97.1	107.0
45	7.66	112.0	124.0
48	8.80	128.0	142.0
52	10.0	146.0	160.0
Reference Specifications: ASTM-A-1023; API 9A			

---